


## **Nickel Metal Hydride Battery**

| SPECIFICATIONS            |  |  |  |
|---------------------------|--|--|--|
| Type Designation          | HR14 40  |  |  |
| Chemical System           | Ni/KOH-H <sub>2</sub> O/MH                                 |  |  |
| Nominal Voltage           | 1.2V   |  |  |
| Approx. Weight            | 74.0g  |  |  |
| Dimensions (mm)           | Diameter: 24.9 ~ 26.2<br>Height: 48.6 ~ 50.0               |  |  |
| Nominal Capacity          | 4000mAh<br>Discharged at 0.2C, 24h/d,<br>20±5°C, e.v.=1.0V |  |  |
| Standard Charge           | 400mA X 16hrs  |  |  |
| Operating<br>Temperature  | Charge: 0°C ~ 45°C<br>Discharge: -20°C ~ 60°C              |  |  |
| Recommended Storage Temp. | -20°C ~ 35°C   |  |  |
|                           |  |  |  |

Packaging materials comply with EU's directive on packaging materials and waste. (94/62/EC)



| Dimensions | 1 | Min. | Max. |
|------------|---|------|------|
|            | Φ | 24.9 | 14.5 |
|            | Α | 48.6 | 50.0 |



## WARNINGS

- Should be charged prior to use
- Use the correct charger for Ni-MH batteries
- Do not reverse charge
- Do not subject to adverse conditions such as extreme temperature, deep cycling and excessive over charge/over discharge

| - PERFORMANCE                           |        |                                |  |   |  |  |  |
|---|--------|--------------------------------|--|---|--|--|--|
| Test                                    | Unit   | Specification                  | Condition  | Remarks   |  |  |  |
| Open Circuit Voltage (OCV)              | V      | ≥ 1.25                         | Within 1hr after standard  | Unit Cell   |  |  |  |
|   |        |                                | charge   |   |  |  |  |
| SERVICE PERFORMANCE                     |        |                                |  |   |  |  |  |
| Standarge Dischage (0.2C <sub>5</sub> ) | minute | ≥ 300                          | Standard Charge, 1hr rest<br>before discharge                      | Up to 3 cycles are allowed. The test shall be terminated at the end of the first cycle which meets the requirement. |  |  |  |
| High Rate Discharge (1C <sub>5</sub> )  | minute | ≥ 48                           | Standard Charge, 1hr rest  |   |  |  |  |
| 3                                       |        |                                | before discharge   |   |  |  |  |
| Charge Retention                        | mAh    | ≥ 2400<br>(60%C <sub>5</sub> ) | Standard Charge<br>Storage 28 days at 20°C.<br>Standard discharge. |   |  |  |  |
| IEC Cycles Test                         | Cycle  | ≥ 500                          | IEC 61951-2  |   |  |  |  |